

IDROCALCE

Waterproofing

- Dehumidifying
- Environment Friendly
- Chromium-Free
- Radon Free
- Restoration
- Breathable
- Resistant
- Versatile
- Healthy
- Anti-Condensing
- Nhl 5
- Highly Adhesive
- Quick
- Reversible
- Easy
- Green Building
- Pollution Resistant
- Waterproof



Technical Data

ELEMENT A:

GRAIN SIZE CURVE (EN 1015-1) 0 - 0.6 mm

pH OF THE MIXTURE > 12.5

APPARENT DENSITY IN PILE 1400 kg/m³

PACKAGING 25 kg bag

PALLET 48 bags, 1200 kg

STORAGE keep in dry place for 18-24 months in original package

ELEMENT B:

DENSITY 1000 kg/m³

MAX VOC IN READY TO USE MATERIAL < 10g/l

ACTIVE PART 40%

PACKAGING 8 l tank

PALLET 48 tanks, 384 kg

STORAGE keep in dry place for 12 months in original package

A+B SYSTEM:

GRAIN SIZE CURVE (EN 1015-1) 0 - 0.6 mm

pH OF THE MIXTURE > 12.5

DRIED MORTAR APPARENT DENSITY (EN 1015-10) 1600 kg/m³

COMPRESSIVE STRENGTH (EN 1015-11) category CS II

ADHESION (EN 1015-12) > 1 N/mm² FP-B

ABSORPTION OF LOW PRESSURED WATER AFTER 60 MINUTES 0 ml/cm²

CONSUMPTION 1.4 kg/m²/mm

APPLICATION TEMPERATURE from + 5°C to +30°C

REACH CLASSIFICATION See SDS