

## NHL 2

---

The NHL2 is a pure white low resistance SAINT-ASTIER Pure Natural Hydraulic Lime, produced by using selected siliceous limestones. The baking of the limestones is carried out in vertical ovens at a temperature below 1250°C and reduced in powder by only the breakdown of calcium oxide, without the need for grinding. NHL 2 is totally devoid of pozzolanic materials, blast furnace slags, flying ash or hydraulic binders of any kind (clinker, cement, etc.), VOCs and according to Standard UNI EN 459-1.

- Dehumidifying
- Environment Friendly
- Disinfectant
- Slag Free
- Chromium-Free
- Radon Free
- Restoration
- Breathable
- Resistant
- Cement Free
- Versatile
- Recyclable
- Without Ashes
- Healthy
- Antibacterial
- Anti-Condensing
- Anti-Mould
- NHL 2



---

## Features

The porosity of Natural Hydraulic Lime NHL 2 guarantees high water vapour diffusion, gives breathability to the substrate, allows the disposal of absorbed water and regulates environmental humidity avoiding the formation of dangerous condensation and moulds. The high basicity of the mixture whose pH is equal to 12.5 makes the surfaces impregnable from biodeteriogenic agents and prevents their proliferation, generating hostile conditions for the survival of pathogenic micro organisms (bacteria, fungi, viruses) causing infections, diseases or allergic reactions. Products obtained with the only NHL 2 binder, being totally mineral; do not constitute "special waste".

---

## Fields of application

Pure Natural Hydraulic Lime NHL 2 can be used directly on the construction site as a mortar binder for stucco, for the consolidation of lesions of murals by injection, mould restoration, restoration of thin joints, adhesion of detached plaster and in all cases where elasticity is a fundamental prerogative. Mortars and plasters obtained using the Pure Natural Hydraulic Lime NHL 2 can be directly applied on vertical and horizontal surfaces consisting of solid bricks, hollow blocks, lightweight hollow blocks, mixed brick, stones and tuff. For all those compact or poorly absorbent surfaces (concrete blocks, expanded clay pebbles, concrete cells, surfaces with a rough lime or cement based layer, R.C. structures, magnesium wood) the use of plaster prepared with lime NHL 2 on the construction site will have to be preceded by the application of SPRIZZO Ponte di Adesione.

## Application

For the preparation of mortar with Pure Natural Hydraulic Lime NHL 2 on the construction site it is essential to use a washed aggregate and free of deliquescent materials, screened with a continuous grain size arc depending on the type of work that has to be carried out. The nature of the aggregate may be of siliceous, carbonate or opus signinum type. The plaster laying consists of Pure Natural Hydraulic Lime NHL 2 must be preceded by the preparation of the substrate: if the surface is compact or slightly absorbent, the application must be preceded by SPRIZZO Ponte di Adesione; for masonry with rising damp the use of SPRIZZO ANTISALE is recommended.

If the substrate is dry, it should be suitably wet except for the surfaces already treated with repairing and restoration mortar SPRIZZO ANTISALE. The spreading of mortars and plasters prepared on the construction site with NHL 2 can be done either manually with a float and trowel or bucket plastering machine, and mechanically with the aid of traditional peristaltic pump or screw plastering machine. The application thickness will be assessed according to the aggregate used.

When applying multiple layers, wait until the previous one has lost a large part of the mixture water and the surface is not compact. If the previously applied plaster layer made of NHL 2 is already dry, proceed with proper wetting of the substrate before applying the following layer. This operation will allow keeping the new layer workable and will ensure perfect ADHESION to the underlying layer.

In order to contain any cracking phenomena which may occur in the zones of geometrical discontinuity or the nature of the substrate it is recommended to place an alkali resistant fibreglass mesh TCS GLASS CK 100. The mesh will be laid in the last cm of the plaster. The ratio between Pure Natural Hydraulic Lime NHL 2 and aggregates can vary from 250 kg/m<sup>3</sup> to 350 kg/m<sup>3</sup> according to the type of intervention implemented or the specific technical requirements of the construction site.

---

## Finishes

The use of a product of the TCS Finishing Line constitutes the natural completion of a compatible cycle with the substrate, particularly with regard to the characteristics of breathability and permeability. The use of the TCS Finishing Line products, made of Lime putty CL 90 or Potassium Silicate, is the obligation to fulfil the expectations of aesthetic and performance features at the basis of the TCS product choice.

## Technical Data

**PRODUCT TYPE:** Pure Natural Hydraulic Lime NHL 2 UNI EN 459-1

---

**CLOURS:** White Brightness Index 76

---

**90 micron FINENESS:** 5%

---

**200 micron FINENESS:** 0.5%

---

**CHEMICAL ANALYSIS**

CaO: 63%; SiO<sub>2</sub> insoluble: 8%; SiO<sub>2</sub> combined: 6%; Al<sub>2</sub>O<sub>3</sub>: 1.3%; Fe<sub>2</sub>O<sub>3</sub>: 0.4%; SO<sub>3</sub>: 0.31%; MgO: 0.75%; MnO: 0.01%; TiO<sub>2</sub>: 0.12%; K<sub>2</sub>O: 0.16%; Na<sub>2</sub>O: 0.04%

---

**pH OF THE MIXTURE** > 12.5

---

**APPARENT DENSITY IN PILE average** 500 kg/m<sup>3</sup>

---

**Ca(OH)<sub>2</sub>** 58%

---

**EXPANSION** < 1 mm

---

**COMPRESSIVE STRENGTH 7 DAYS (EN 1015-11)** 2 MPa

---

**COMPRESSIVE STRENGTH 28 DAYS (EN 1015-11)** 3-4 MPa

---

**PENETRATION** 22.5 mm

---

**LOSS ON IGNITION** 20%

---

**CURING TIME:** 6 h

---

**FLAME RESISTANCE (EN 13501-1):** A1 class

---

**CONSUMPTION:** 250-350 kg/m<sup>3</sup> aggregate

---

**PACKAGING:** 25 kg bag

---

**PALLET:** 40 bags, 1000 kg

---

**STORAGE:** keep in dry place for 18-24 months in original package

---

**APPLICATION TEMPERATURE:** from + 5°C to +32°C

---

**REACH CLASSIFICATION:** See SDS