

STORICAL MARMO LUSTRO

STORICAL MARMO LUSTRO è un tonachino minerale biocompatibile, in pasta pronto all'uso. Composto da polvere impalpabile di marmo e grassello di calce ottenuto per cottura di calcari puri in forni verticali a temperature inferiori a 900°C, classificato con la sigla CL 90- S PL conforme alla norma UNI EN 459-1. Il prodotto è disponibile bianco o colorato nella massa con pigmenti inorganici resistenti alla luce per l'esecuzione di rasature di pregio che presentano particolari effetti cromatici, di lucentezza e compattezza.

- Dehumidifying
- Environment Friendly
- Disinfectant
- Restoration
- Breathable
- Resistant
- Versatile
- Recyclable
- Healthy
- Antibacterial
- Anti-Condensing
- Anti-Mould
- Highly Adhesive
- Quick
- Reversible
- Green Building
- Pollution Resistant
- CL90



Features

STORICAL MARMO LUSTRO is made of marble powder and, as the only binder, lime putty CL 90-S PL long cured and totally hydrated. This composition makes the finish eco-friendly, biocompatible and reversible. The absence of volatile organic compounds (VOCs) ensures the purity while the total lack of petrochemical derivative products ensures compatibility with full respect for man and the environment by eliminating Sick Building Syndrome. The totally mineral nature of STORICAL MARMO LUSTRO, combined with a very basic pH, makes it an excellent natural protection against bacterial proliferation and the formation of superficial moulds, avoiding the formation of dangerous condensation by regulating the ambient humidity and the carbon dioxide content of environments. The TCS COLOURS are available in the fan colour guide, in white, or to the sample. The surfaces obtained with STORICAL MARMO LUSTRO are colours, special shades obtained by the appropriate use of polishing tools.

Fields of Application

STORICAL MARMO LUSTRO is specially designed for smooth, compact and mirror-polished levelling of high quality in the newly constructed, recovering existing structure and restoration sector. It is easily workable with the traditionally used techniques in applying plaster made of lime and marble powder. It can be applied to different types of vertical and horizontal substrates, internal and external, both existing and new, such as: rustic plaster of any type and nature (lime and/or cement based) previously smoothed with the products of the TCS Smoothing Compound Line.

Application

In order to obtain excellent results, it is recommended to apply STORICAL MARMO LUSTRO on surfaces previously smoothed with the TCS Smoothing Compound Line products. In the case of absorbent, clean and cohesive surfaces, the application of STORICAL MARMO LUSTRO can take place directly without regulating primers. Otherwise, for poorly cohesive, very absorbent or particularly uneven supports, surface treatment with KAPPASIL FONDO diluted with water up to 50% is recommended. Adequate wetting of the substrate is recommended where it is deemed necessary.

STORICAL MARMO LUSTRO can be applied manually in two coats. If deemed necessary, it can be mixed in the original package with a vortical whip at low speed. STORICAL MARMO LUSTRO is ready to use and does not require any kind of addition. The spreading will be carried out with the aid of an American steel spatula with round edges and trowel, making sure to obtain an even surface and free of imperfections. The following coats should be given after the drying of the previous one, until the desired effect is obtained. Then the counterbore and polishing operations will follow which will give the surface a compact and mirror-polished appearance.

The spreading of STORICAL MARMO LUSTRO on large surfaces will have to be carried out without interruptions to avoid the unaesthetic reworking of the laying. In fact, in addition to the temperature, the relative humidity also greatly influences the final result: both factors influence the drying timings by modifying the chromatic yields of the material.

Finishes

Surfaces treated with STORICAL MARMO LUSTRO will have to be suitably protected with the protective spreading of the ANTICA CERA '500 paste. In the case where STORICAL MARMO LUSTRO is laid on particularly exposed external surfaces, it is recommended to apply a waterproof protection type T1 10 or T1 10 PLUS of the TCS Protection Line.

Warnings

- Product for professional use.
- Do not modify the product.
- Store the product in a dry place in the original sealed packages.
- Before using the product refer to the Safety Data Sheet.
- The data given correspond to the technical and application knowledge we have for proper use of the product, so it is recommended to carry out a practical test prior to in order to verify the suitability of the product for its intended use and consumption.
- Protect the surfaces from atmospheric phenomena, sun, wind, rain and frost.
- Since our company is not the executor of the works and can not intervene directly on the construction site conditions and on the methods of work execution, the indications given are to be considered as indicative and general, and therefore not binding for the same.
- The Company reserves the right to make the changes at any time without notice when it deems necessary.
- For more information and practical product demonstrations please consult our technical service.
- Always refer to the updated versions of the technical data sheets available at www.tcs-srl.it.

Technical Data

PRODUCT TYPE Air Lime intonachino plaster finish CL90-S PL UNI EN 459-1 for interior and exterior use

pH OF THE MIXTURE >12.5

DENSITY 1750 kg/m³

DRY RESIDUE 75 +/- 1% by weight

2010 CE LIMIT VALUE OF VOC (cat. A/a) 30 g/l Max VOC 28 g/l

WATER VAPOUR PERMEABILITY COEFFICIENT (EN 1015-19) Sd 0,25 m

DRYING at 20°C and 60% R.H. to the touch at 8-10 hours completed in 24-36 hrs

FLAME RESISTANCE (EN 13501-1) A1 class

DILUTION ready to use

COMPATIBILITY not compatible with other products

CONSUMPTION 1,2kg/m² two coats on new civil support

APPLICATION steel spatula

CLOURS the TCS COLOURS are available in the fan colour guide, in white or to the sample.

PACKAGING 25 kg bucket

PALLET 36 buckets, 900 kg

STORAGE without expiration stored in original unopened packages in a dry place away from sources of heat and frost

APPLICATION TEMPERATURE from +5°C to +32° C

REACH CLASSIFICATION See SDS